## CLOUD 9 CIRRUS 9mm

PRODUCT DATASHEET • ISSUE 7 - 28.11.20

## **FEATURES**

- MANUFACTURED IN THE UK TO BS EN 14499
- EXCELLENT THERMAL AND SOUND REDUCTION PROPERTIES
- EXCELLENT RECOVERY CHARACTERISTICS

## **APPLICATIONS**

- DOMESTIC INSTALLATIONS
- LUXURY USE AREAS
- AREAS OF MEDIUM WEAR
- SUITABLE FOR WOOD BLOCK FLOORS

CLOUD
RANGE OF UNDERLAYS®
ALEAR

STANDARD SPECIFICATIONS				
CORE	Cloud 9 APT Crumb			
TOP SURFACE	Printed stitch bonded crepe paper			
BOTTOM SURFACE	White non-woven fabric			
NOMINAL THICKNESS	9.00 mm			
NOMINAL ROLL WEIGHT	15.7 kg	34.6 lb		
WEIGHT PER UNIT AREA	1042 g/m²	31 oz/yd²		
ROLL LENGTH	11.0 m	36.0 ft		
ROLLWIDTH	1.37 m	54 in		
CORE DENSITY	100 kg/m³			
PRODUCT DENSITY	116 kg/m³			
ROLL WIDTH CORE DENSITY	1.37 m 100 kg/m³			

BS EN 14499:2015 TEST RESULTS - UK AND EU STANDARD FOR CARPET UNDERLAYS				
END USE CLASSIFICATION	BS EN 14499	L/U		
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS 4098	>150 J/m <sup>2</sup>		
RETENTION OF WORK OF COMPRESSION	BS 4098	>80 %		
LOSS IN THICKNESS AFTER STATIC LOADING	BS 4939 ISO 3416	<5.00 %		
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS ISO 2094 (R05)	<5.00 %		
RESISTANCE TO CRACKING	BS EN 14499	Pass		

INDOOR AIR QUALITY TEST		
TESTED TO ISO 16000		
TESTED TO EUROFINS INDOOR AIR COMFORT® STANDARD	Pass	
TESTED TO EUROFINS INDOOR AIR COMFORT GOLD® STANDARD	Pass	ÉMISSIONS DANS L'AIR INTÉRIEUR
FRENCH VOC REGULATIONS	A+	A+
FRENCH CMR COMPONENTS	Pass	
ITALIAN CAM	Pass	
AgBB/ABG	Pass	
FORMALDEHYDE EMISSION CLASS	E1	
BREEAM INTERNATIONAL	Compliant	
LEED V4 (OUTSIDE U.S.)	Compliant	
BREEAM <sup>®</sup> NOR	Compliant	

OTHER RELEVANT TESTS				
THERMAL RESISTANCE (TOG RATING)	BS 4745	2.5 Tog		
IMPACT SOUND IMPROVEMENT INDEX (TESTED / RATED)	BS EN ISO 10140-3 BS EN ISO 717-2	39-41 dB		

## DISCLAIMER

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball & Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.

