Technical specifications

Sarlon 15 dB, Sarlon 19 dB and Modul'up 19 dB meet the requirements of EN 651 and ISO 11638 Modul'up Compact meets the requirements of EN 10582

Sarlon 15 dB

Sarlon 19 dB



Modul'up Compact

Modul'up 19 dB

	Total thickness	EN ISO 24346	2.6 mm	3.4 mm	3.45 mm	2.0 mm
	Wear layer thickness	EN ISO 24340	0.70 mm	0.70 mm	0.70 mm	0.70 mm
######################################	Commercial use	EN ISO 10874	34	34	34	34
Thu 🏌	Industrial use	EN ISO 10874	42	42	42	43
	Packaging		Rolls	Rolls	Rolls	Rolls
	Roll length	EN ISO 24341	+/- 25 ml	+/- 25 ml	+/- 25 ml	+/- 25 ml
	Roll width	EN ISO 24341	2 m	2 m	2 m	2 m
	Total weight	EN ISO 23997	2,700 g/m ²	2,900 g/m²	2,830 g/m	2,600 g/m
	Impact sound reduction	EN ISO 717-2	$\Delta Lw = 15 dB$	$\Delta Lw = 19 dB$	$\Delta Lw = 19 dB$	$\Delta Lw = 4 dB$
	In-room impact noise	NF S 31-074	Ln,e,w < 65 dB, Class A	Ln,e,w < 65 dB, Class A	Ln,e,w < 65 dB, Class A	Ln,e,w < 75 dB, Class B
(a)	Sound absorption	EN ISO 354 EN ISO 11654	$\alpha_{_{\scriptscriptstyle W}}=\pm~0.05$	$\alpha_{_W} = \pm \ 0.05$	$\alpha_{_W}^{}=\pm~0.05$	$\alpha_{_{\rm W}} = \pm 0.05$
	Residual indentation (Typical value) <i>Requirement</i>	EN ISO 24343-1	0.05 mm ≤ 0.20 mm	0.08 mm ≤ 0.20 mm	0.08 mm ≤ 0.20 mm	0.02 mm ≤ 0.10 mm
96	Slip resistance	DIN 51130	R10	R10	R10	R10
	Abrasion resistance	EN 660-2	Т	Т	Т	T
	Castor chair resistance	ISO 4918	Yes	Yes	Yes	Yes
	Furniture leg resistance	EN ISO 16581	compliant	compliant	compliant	compliant
K Z	Dimension stability	EN ISO 23999	≤ 0.10%	≤ 0.10%	≤ 0.10%	≤ 0.10%
	Colour fastness to light Requirement	EN ISO 105-B02	7 ≥6	7 ≥6	7 ≥6	7 ≥6
	Stain resistance	EN ISO 26987	Excellent	Excellent	Excellent	Excellent
9	Anti-bacterial activity (3)	ISO 22196 or ISO 846	>99% inhibits growth	>99% inhibits growth	>99% inhibits growth	>99% inhibits growth
	Surface treatment		XtremPUR™	XtremPUR™	XtremPUR™	XtremPUR™
	Emissions into air : TVOC* at 28 days	EN 16516	≤ 0.01 mg/m³	≤ 0.01 mg/m³	≤ 0.02 mg/m³	≤ 0.02 mg/m³
	Creating better environme	nts				
	Renewable electricity	to the Floor Installation off cuts can be collected via Back to the Floor. Modul'up is recyclable at end of life				
back to the floor program reduct thereing	Back to the Floor					
	Ska rating					
	REACH (European regulation)	1907/2006/CE	compliant (1)	compliant (1)	compliant (1)	compliant (1)
(€	Compliance EN 14041		0200860-DOP-010	0200859-DOP-010	0200859-DOP-010	0200862-DOP-010
L Brist NCS	Reaction to fire	EN 13501-1	B _{fl} - s1, L, NCS	B _{fl} - s1, L, NCS	B _{fl} - s1, L, NCS	B _{fl} - s1, L, NCS
9/3 0s	Slip resistance	EN 13893	$\mu \ge 0.30$	$\mu \ge 0.30$	μ ≥ 0.30	μ≥ 0.30
75 Å	Body voltage	ISO 1815	≤ 2 kV	≤ 2 kV	≤ 2 kV	≤ 2 kV
	Thermal conductivity (2)	EN 12524 (EN ISO 10456)	0.25 W/(m.K)	0.25 W/(m.K)	0.25 W/(m.K)	0.25 W/(m.K)

(1) The articles (products) do not contain substances of the candidate list published by ECHA (SVHC substances of very high concern) to be declared in accordance with REACH.

Recommended adhesives: For the latest installation instructions and recommended adhesives please visit **www.forbo-flooring.co.uk/installation**

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.

All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.

The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites.

Sarlon and Modul'up are manufactured in a facility certified to SA8000° and ISO 45001.





Whilst Forbo Flooring UK Limited does its best to ensure that the contents of this specification are correct and accurate at the time of publication, to the fullest extent permitted by law, Forbo Flooring UK Limited makes no, and expressly disclaims all, guarantees of any kind, express or implied in respect of the information, content, materials or products displayed in this specification and does not represent that the information is accurate, complete or current.





For more information:

e: info.flooring.uk@forbo.com

t: **0800 0282 162**

w: forbo-flooring.co.uk/sarlon



⁽²⁾ The products are suitable for underfloor heating.

⁽³⁾ To strictly follow the Forbo cleaning recommendation process is the best protection against infection. Please visit www.forbo-flooring.co.uk/acousticdownloads to access our full Cleaning and Maintenance instructions.

^{*} TVOC : total volatile organic compounds.